



SMR/DL 02	1	
Date Issue	4. NUV 33	

turbo set

Ultra-rapid setting, flexible cementitious wall & floor tile

DESCRIPTION

Highly polymer-modified water/frost-resistant cementitious extremely rapid-setting tile adhesive for walls and floors.

Use for

- Fixing ceramics; porcelain and vitrified tiles; mosaics; certain types of natural stone including marble, terrazzo and granite; rigid foam insulating materials and brick slips in dry or wet interior and exterior environments.
- Certain types of natural stone (i.e. limestone, travertine, granite and some marble) may be susceptible to staining. In this case, use of a BAL rapid-setting white adhesive e.g. BAL TURBO SET WHITE or BAL RAPID-FLEX FIBRE PLUS is recommended.
- Recommended for total immersion areas/showers. Also suitable for installations subject to limited movement and vibration.
- Heated screeds.

Restrictions: NOT suitable for

 Metal, painted, Glass/metal tiles with water-sensitive coating on back, plywood walls, existing glazed tiles**, (3m x 1m in size) and large areas to tile.

Key

*Further applications possible by adding BAL ALL IN ONE PLUS to provide flexibility, increased adhesion and reduce water permeability. This enables use onto glazed surfaces.

USAGE: Bed Thickness / Time at 20°C

Bed	Open	Pot Life	Setting
Thickness ^	Time**		Time**
2 to 10mm^	10 min	15 min	30 min

** Times will be extended in colder temperatures, when fixing to impervious backgrounds or when fixing tiles of low porosity.

^ Use minimum 3mm thickness for floor tiling.

^ typical application 2-10mm, use up to 15mm in isolated areas

PRODUCT INFORMATION

Composition: Highly polymer-modified cement-based powder. *(available at Topps Tiles only)*

Colours: Grey & White.

Type/Classification: Exceeds BS EN 12004 **C2F** – Cementitious Adhesive with Improved / Additional Characteristics, Fast Setting.

Pack sizes: 5kg

Key Features:

- Allows fast track completion of projects with the ability to grout tiles after just 30 minutes at 20°C (working time 15 minutes).
- Ideal to finish last 1-2m² of tiling to allow same day grouting or to fast-track minor repairs.
- Flexible; Suitable for most backgrounds and for installations subject to limited movement/vibration and heated screeds.
- Enhanced adhesion to fully vitrified/ porcelain tiles and low porosity substrates.
- Highly water/frost resistant.

Grout After: 30 minutes (at 20°C)

COVERAGE

Area	Trowel	Coverage ^^
Dry Wall	6mm Notched	0.5m ² per kg
Wet Wall	6mm Notched (solid bed)	0.4m ² per kg
Exteriors /	10mm Notched	0.26m ² per kg
Floors	(solid bed)	

^^ May vary dependent on nature and flatness of surface, and on trowel used.

TEMPERATURE RESISTANCE***

-30°C to 100°C *** Cured adhesive.

SURFACE PREPARATION

General

Ensure surfaces to be tiled are flat, clean, dry, sound, free from contamination and all barriers to adhesion. Surface regularity:

Surface Regularity is defined as the deviation in height of the surface of a flooring layer over short distances in a local area. In simpler terms, it is the 'flatness' or 'measure of unevenness' of the surface.

Class	MAXIMUM	APPLICATION
	PERMISSABLE	
	DEVIATION - 2M	
	STRAIGHT EDGE (MM)	
SR1	3mm	Recommended for direct
		fixing of tiles and slabs
		with a tile adhesive

N.B. When using larger format tiles, it is essential that the substrate is as level as possible, ideally better than SR1, as this will avoid excessive bedding out of adhesive.

In wet areas: waterproof background with BAL WATERPROOF PLUS, BAL WATERPROOFING KIT FOR SHOWERS or BAL WP1 TANKING SYSTEM.

If tiling externally, provide protection against inclement weather during fixing and grouting and for as long as possible afterwards. It is recommended that all direct to earth sub floors include a DPM or, if required a surface DPM can be applied prior to tiling *See BAL DPM TECHNICAL DATA SHEET for further details.*

SUITABLE SURFACES include:

Plaster (finish coat only)

Must be at least 4 weeks old before tiling. Ensure that the plaster is free from dust, laitance, and friable material. If *plaster is shiny or polished*, brush thoroughly with a stiff bristled brush.

The plaster must always be primed with 2 coats of (second coat applied at 90° to the first):

BAL ALL IN ONE PLUS (diluted 1:2 by volume with clean water)

Allow each coat of primer to dry.

 $\label{eq:maximum 20kg/m^2} \mbox{ weight restriction for tiling onto plaster.} \\ \mbox{ Note: The use of plaster is not recommended in commercial wet rooms or domestic power showers.} \\$

Plasterboard

Ensure boards are dry, securely fixed and rigid and suitable thickness used.

Maximum 32kg/m² weight restriction for tiling onto

plasterboard. NOTE: For higher weight tolerances use a suitable board.

Note: The use of plasterboard is not recommended in commercial wet rooms or domestic power showers.

Lightweight blockwork/walling

Allow new block mortar to dry for minimum 6 weeks before rendering (such as BAL QUICKSET RENDER)/plastering or a suitable tile backer board.

BACKGROUNDS / BASES

Brick/Concrete (2)	\checkmark	Plaster (3) (5)	<
Rendering (3)	\checkmark	Plasterboard (5)	\checkmark
Tile Backer/Fibre	\checkmark	Unglazed Ceramic	\checkmark
Cement Boards		Tiles / Hard Natural	
(3)(4)(5)(9)(11)		Stone (4)(11)	
Cement:Sand Screed	\checkmark	Lightweight	✓
(3)(4)(11)		Blockwork (12)	
Anhydrite/Calcium	\checkmark	Overlaid Timber	✓
Sulfate Screeds		Floors – 15mm min.	
(4)(8)(11)		(3)(4)(5)(6)(11)	
Mastic Asphalt (7)	\checkmark	Timber Floors	✓
(4)(11)		(3)(4)(10)	
Vinyl Tiles/Sheets	\checkmark	Glazed Tiles	×
(4)(11)			

USAGE & SERVICE CONDITIONS

Walls	\checkmark	Floor	\checkmark
Interior	\checkmark	External	✓
Dry	\checkmark	Wet Areas	✓
Worktops (1)	\checkmark	Showers (a)(5)	✓
Swimming Pools (b)(c)	~	Hydrotherapy Pools (b)(c)(1)	~
Underfloor Heating Systems (3)(4)(9)(10)	✓	Limited Movement/Vibration (4)(11)	~

(1) Tiles must be grouted using BAL ABSOLUTE GROUT.

(2) Provided the surface is sufficiently flat.

(3) Prime with BAL ALL IN ONE PLUS. (See BAL TECHNICAL DATA SHEET for more information).

(4) Do not need to prime when using BAL FLEXBONE 2Easy uncoupling mat.

(5) In wet conditions tank out with BAL WATERPROOF PLUS or BAL WATERPROOF 1C.

(6) Seal back face and edges with undiluted BAL ALL IN ONE PLUS.

(7) Flooring grade only.

(8) Prime with BAL ALL IN ONE PLUS, first coat 1:4 with

water by volume, second coat diluted 1:2 with water, $90^{\rm o}\,{\rm to}$ the first coat.

(9) Check suitability for the intended purpose with the

manufacturer or check BAL TECHNICAL DATA SHEETS on any BAL Products.

(10) When using BAL uncoupling systems (See Technical Data Sheets).

(11) May be used in conjunction with BAL RAPID-MAT or BAL FLEXBONE 2Easy uncoupling mats.

(12) Apply a cement: sand render e.g. BAL QUICKSET RENDER or a suitable tile backing board prior to tiling.

Note:

(a) Do not use shower for at least 2 weeks after completion of grouting – as per latest BS 5385:Part 4.

(b) Do not fill pool for at least 3 weeks after completion of grouting – as per latest BS 5385:Part 4. BAL TURBO SET is sulphate resistant.

(c)Must be onto a watertight background.

Turbo Set

Dense concrete/blockwork walling

Allow new block mortar to dry for minimum 6 weeks before rendering (such as BAL QUICKSET RENDER) /plastering.direct fixing tiles, wall must be smooth-faced and sufficiently flat (SR1).

Concrete; cement:sand screeds and rendering

Before tiling, ensure that the substrate is flat (SR1), free from efflorescence, laitance, dirt, polished concrete and other loose materials. Remove using suitable mechanical methods (see BAL TECHNICAL DATA SHEET on BAL ALL IN ONE PLUS for priming information). NOTE: Priming and sanding is not required when using BAL FLEXBONE 2Easy. Allow the following minimum drying times:

- Concrete/concrete block walls/clay brickwork: 6 weeks

- Cement:sand screed: 3 weeks

Cement:sand rendering: 2 weeks (3 weeks for swimming pools)

BAL QUICKSET CEMENT:sand screeds and rendering

- Bonded screeds: 4 hours**

- Unbonded/floating screeds: 48 hours

- Rendering (bonded): 4 hours**

BAL ALL IN ONE PLUS SLURRY

**1 part sand to 1 part BAL QUICKSET CEMENT by weight, mixed with appropriate amount of BAL ALL IN ONE PLUS prediluted 1:1 with clean cold water by volume to achieve desired consistency.

BAL QUICKSET RENDER: 2 hours

Asphalt (Flooring grade only)

Must be of a suitable grade, be clean, in sound condition (without brittleness, softening. etc.) and have adequate cohesive strength, a natural float finish and laid on a firm rigid base.

Ensure that surface is sufficiently regular to suit bedding depths of adhesive.

Clean thoroughly to remove surface dirt using warm water and a suitable detergent. Remove all detergent residues with clean water.

Fibre reinforced cement boards and lightweight tile backer boards (Walls)

Install boards to latest BS 5385 Part 3 – i.e. moistureresistant boards and screwed to seasoned timber or suitable proprietary framework at maximum 300mm centres vertically and horizontally or as per the board manufacturer's recommendations. Ensure no fixings protrude.

Some boards may require priming, prior to tiling with a cementitious based tile adhesive. Use a suitable primer such as BAL ALL IN ONE PLUS diluted 1:4 with clean cold water. *Please refer to the BAL TECHNICAL DATA SHEETS for further information.*

IMPORTANT NOTE: Obtain manufacturer's confirmation that boards are suitable for the tiling application and for relevant fixing instructions.

Anhydrite/calcium sulfate and hemi-hydrate screed

Allow the screed to dry out in accordance with manufacturer's instruction example: moisture contact below 0.5% w/w or 75% RH (Relative Humidity). Mechanically abrade the top surface to remove weak/dusty surface layer(s) as per the screed manufacturer's recommendations. Remove all dust and loose material e.g. by vacuum etc. before priming with 2 coats of (second coat applied at 90° to the first): – BAL ALL IN ONE PLUS diluted 1:4 with clean water and

second coat diluted 1:2 with clean water. Allow each coat of primer to dry.

NOTE: For further information on other backgrounds and preparation, contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.

Using onto BAL FLEXBONE 2Easy over

Anhydrite/calcium sulfate and hemi-hydrate screed

Allow the screed to dry in accordance with manufacture's instruction example: moisture contact below 1.5% w/w. No need to mechanically remove the top surface. The floor must be flat to SR1 and the only preparation is to sweep the floor. No priming required. *NOTE: For further information contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE and* see BAL TECHNICAL DATA SHEET on BAL FLEXBONE for further guidance.

Overlaid timber floors (min. 15mm)

Ensure timber floor (i) is sufficiently rigid and stable to receive tiles; (ii) can carry the additional static and dynamic load without excessive deflection; and (iii) has adequate ventilation under the timber.

Overlay existing timber floor with e.g. a suitable waterresistant grade e.g. marine plywood, min. 15mm thick, screwed (not nailed) at 300mm centres.

Seal timber surface on the underside and edges with undiluted BAL ALL IN ONE PLUS.

Before tiling prime the surface with 2 coats of BAL ALL IN ONE PLUS diluted 1:2 with clean cold water.

Allow to dry. *NOTE: Timber is not a suitable base for floor tiling in wet, frequently damp, or*

high humidity areas, unless appropriate precautions are taken (see BS 5385-4). BS 5385 -3.

Tongued and grooved floorboards with BAL RAPID-MAT or BAL FLEXBONE 2Easy

Ensure boards are flat (SR1) dry, rigid, and securely fixed (screwed to joints at 300mm centres, including any crossnoggins, if necessary). Sand (abrade) surface and ensure any surface coatings removed, e.g. varnish, lacquers, etc. Before priming with 2 coats of (second coat applied at 90° to the first):

BAL ALL IN ONE PLUS (diluted 1:2 by volume with clean cold water)

Allow each coat of primer to dry. *NOTE: Priming/sanding is not required when using BAL FLEXBONE 2Easy.*

If necessary, the floor may require levelling using a suitable leveller such as BAL LEVEL MAX and allow to dry before installing BAL RAPID-MAT or BAL FLEXBONE 2Easy. See BAL TECHNICAL DATA SHEET for further information on suitable surfaces and application.

Existing Unglazed ceramic tiles, quarry tiles, terrazzo and natural stone

For wall ensure existing tiles/stone are soundly bonded to a stable background that is sufficiently strong enough to support the weight of the new tiling.

For floors ensure that the existing finish is firmly adhered to the base.

If areas are loose or hollow-sounding, remove and make good with BAL QUICKSET RENDER or 1:3 cement:sand mortar over a slurry bonding coat (1 part sand to 1 part cement by weight, mixed with appropriate amount of BAL ALL IN ONE PLUS pre-diluted 1:1 by volume with clean cold water to achieve desired consistency).

Existing vinyl tiles

Ensure these are in good sound condition and securely bonded to their base.

Remove loose or damaged tiles/areas of sheet along with any loose or soft adhesive.

Remove any polishes, wax, grease etc. with a suitable proprietary cleaner.

NOTE: Cushioned types of flooring are not suitable and must be completely removed along with the adhesive residue prior to tiling.

Metal

Suitable to be used with metal when primed with aggregate blinded **BAL DPM**. *See BAL TECHNICAL DATA SHEET for further details*.

Heated Screeds

Suitable for sand/cement screeds with water fed underfloor heating encased within. Use in conjunction with one of the BAL uncoupling mattings, depending upon the size and type of tiles. *NOTE: For further information on other backgrounds and preparation, contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.*

APPLICATION/USAGE

Do NOT use in temperatures below 5°C or in damp conditions.

Trowel recommendations

Area	Trowel
Internal Dry Wall Area (up	Min 6mm Notched Trowel
to 300x300mm tiles)	
Internal Wet Wall Area (up	Min 6mm Notched Solid
to 300x300mm tiles)	Bed Trowel
External & Walls and Floors	Min 10mm Notched Solid
	Bed Trowel
Mosaics (up to 100x100mm	Min 4mm Notched Trowel
tiles) including when used	
with BAL RAPID-MAT/BAL	
FLEXBONE VAried)	

NOTE: ensure you achieve the correct contact & thickness of adhesive to both the background and tile in line with BS 5385, Parts 1-5.

NOTE: Follow guidelines to BS Standards (minimum 2mm joints for walls and 3mm for floors, size can change depending on size of tile and environments).

Undertile electrical heating systems

Can be used onto electrical undertile heating systems encased within an appropriate BAL leveller. Over suitable boards/water resistant grade plywood overlays (minimum 15mm thickness) use a suitable leveller such as BAL LEVEL MAX. Consideration may be given to the use of BAL uncoupling mattings, depending upon the size and type of tiles.

BAL LEVELLER	THICKNESS	SETTING TIME
BAL LEVEL MAX	2mm – 80mm*	3 – 4 hours
BAL ACRYBASE	Up to 20mm	3 – 4 hours

See BAL TECHNICAL DATA SHEET for further information on suitable surfaces and application. *Up to 80mm in localised areas only. Thicker layers must also be tiled within 48 hours.

MIXING

Use a BAL MIXING BUCKET or other suitable bucket. 1. Add approximately 2.5 parts powder to 1 part clean cold water by weight. (see table) Never add more water than recommended as this may lead to excess shrinkage or debonding.

2. Mix until lump-free mortar achieved.

3. Allow mixed adhesive to stand for 2 minutes before remixing for 30 seconds. *If using electric drill mixer, blend at slow speed (i.e. under 300rpm).*

Product Size	Usage	Approx. clean cold water required per size
5kg	Wall & Floor Tiling	1 litre

Ready for immediate use. Pot life at 20°C: approx. 15 minutes. NOTE: Pot life/setting time will vary slightly with temperature: higher temperatures = shorter; lower temperatures = longer.

4. Occasionally lift a mosaic/tile to check adhesive contact area. When solid bed fixing, leave no voids behind tiles.

5. Leave adequate joints between individual tiles. Install movement joints to BS 5385, Parts 1-5.

6. Clean off surplus adhesive from tile face and between tile joints before the adhesive has dried.

BAL TURBO SET tile adhesive may be applied on walls and floors using a suitable notched trowel. N.B. For larger format tiles, the reverse of the tile should be back buttered with a thin layer of adhesive to ensure solid bedding. *NOTE: For thick applications, the mixing water should be reduced to achieve the necessary slump resistance.* Do not use thicker beds of adhesive with porous or soft bodied tiles. *Note that when fixing large format tiles, it is essential that the substrate is level better than SR1 to avoid excessive bedding-out of the adhesive and reduce installation time.*

Fixing procedure

1. Apply adhesive to wall or floor surface and comb to required bed thickness ensuring the ribs of adhesive all run in one direction. The adhesive may be applied to a bed thickness of 2 - 10mm or up to 15mm in limited, localised areas. (i.e.MAX 0.5m²)

If fixing large/heavily patterned tiles, apply additional adhesive to tile reverse.

2. *For mosaics*: using a rubber tile float, press mosaics into adhesive and beat into required position.

For tiles: press tile firmly into the ribs of the adhesive and into position, with slight twisting/sliding action to ensure optimum adhesive contact.

3. Fix mosaics/tiles before adhesive forms skin (typically up to 10 minutes at 20°C, depending on surface porosity /atmospheric conditions). If skin has formed, remove adhesive, and apply fresh layer). Discard any adhesive that has begun to set. Do not add further water.

Grouting

1. Wait minimum 30 minutes (at 20°C) after tile fixing. Select a BAL cementitious such as BAL MICROMAX3 ECO GROUT or an epoxy grout such as BAL ABSOLUTE GROUT.

If using paper-faced mosaics: Pre-grout sheet and remove surplus. Place in position and tap down to achieve full contact with adhesive. Ensure joints between sheets match joints between mosaic tesserae (i.e. staggered). Wet paper and carefully remove before adhesive fully hardens. Clean off surplus adhesive and grout from mosaic face. Finish grouting.

2. Fill movement joints with suitable sealant i.e. BAL MICROMAX SEALANT. *However*, do NOT use on sensitive surfaces that could react to acetic acids released during cure. *For intermediate movement joints*, a more durable hardwearing material may be needed e.g. an epoxy polysulphide sealant or a suitable pre-formed movement joint strip.

NOTE: If completing a swimming pool, do NOT fill pool for at least 3 weeks after grouting (contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE for further advice). If completing a shower, do NOT use shower for at least 2 weeks (as required by latest version of BS 5385: Part 4 clause 7.2.1).

HEALTH & SAFETY INFORMATION / GOOD PRACTICE ADVICE

For detailed information and safety guidance, please refer to Product Material Safety Data Sheet [MSDS].

TECHNICAL ADVISORY SERVICE

For free expert guidance on use of this product, or any aspect of tiling, contact the BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE on Tel: 03330 030160 or Email: info@building-adhesives.com

SHELF LIFE

12 months under normal dry conditions. Protect from frost and damp.

QUALITY AND ENVIRONMENTAL STANDARDS

Manufacturing quality assurance standards conform to BS EN ISO 9001. Satisfies the environmental management requirements and operational scope of ISO 14001.

25 YEAR GUARANTEE

All BAL products are supplied with a 25-year product guarantee to be free from manufacturing defects and to be fit for purpose. The guarantee covers materials replacement costs and labour. This guarantee is subject to use of product in accordance with BAL's instructions and technical data, and good working practice. No liability can be accepted for any loss or damage arising from incorrect use of products or poor workmanship, over which BAL has no control. While products may be suitable for installations internally or externally, products when used externally are exempt from cover under the BAL 25 Year Guarantee. Terms and conditions apply. Full details are available for your review at <u>www.bal-</u> adhesives.com

CONDITIONS OF SALE

Sold subject to the Company's Conditions of Sale. Available on request.

For sales and technical queries, contact:

BUILDING ADHESIVES LTD

Longton Road, Trentham, Stoke-on-Trent, ST4 8JB, England www.bal-adhesives.com

Sales Tel: +44 (0) 1782 591160 Fax: +44 (0) 1782 591131

Technical Tel: +44 (0) 3330 030160 Email: info@building-adhesives.com

Ireland Unit 622, Phase III Northwest Business Park Ballycoolin, Dublin 15, Ireland Tel: +353 (0) 1 880 9210 Fax: +353 (0) 1 880 9211

NOTE: BAL reserves the right to update instructions, technical data and other information at any time without notice. PorcelBond Plus[™] is a trademark of Building Adhesives Ltd

Turbo Set